

Technical Data Sheet

Polyflam RPP 1174

Polypropylene
 LyondellBasell Industries
 Engineering Plastics

Product Description

PP Mineral Filled Flame Retardant Contains PBDE

General

- | | |
|-----------------|----------------------|
| Material Status | • Commercial: Active |
| Availability | • North America |
| Features | • Flame Retardant |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.37	1.37 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	3050 psi	21.0 MPa	ASTM D638
Tensile Elongation ¹ (Break)	30 %	30 %	ASTM D638
Flexural Modulus ²	319000 psi	2200 MPa	ASTM D790
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	239 °F	115 °C	
264 Psi (1.8 Mpa), Unannealed	140 °F	60.0 °C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating	V-0	V-0	UL 94

Notes

¹ 2.0 in/min (50 mm/min)

² 0.051 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.