

Technical Data Sheet

Polyflam RPP 371ND

Polypropylene
LyondellBasell Industries
Engineering Plastics

Product Description

PP Mineral Filled Flame Retardant Non-PBDE-Free

General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Mineral, 19% Filler by Weight
Features	<ul style="list-style-type: none"> Flame Retardant

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.36	1.36 g/cm ³	ASTM D792

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	3050 psi	21.0 MPa	ASTM D638
Tensile Elongation ¹ (Break)	30 %	30 %	ASTM D638
Flexural Modulus ²	392000 psi	2700 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.60 ft·lb/in	32 J/m	ASTM D256


Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating	V-0	V-0	UL 94

Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
Filler Content	19 %	19 %	ASTM D5630

Technical Data Sheet

Polyflam RPP 371ND

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.