

Technical Data Sheet  
**POLYFORT® FPP 3725**  
 Polypropylene  
 Engineering Plastics



**Product Description**

PP 40% Glass Fiber Chemically Coupled

**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 42% Filler by Weight
Features	• Chemically Coupled
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.26	1.26 g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength <sup>1</sup> (Yield)	11900 psi	82.0 MPa	ASTM D638
Flexural Modulus <sup>2</sup>	1.09E+6 psi	7500 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.0 ft·lb/in	160 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	298 °F	148 °C	ASTM D648
Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
Filler Content	42 %	42 %	ASTM D5630

**Notes**  
<sup>1</sup> 2.0 in/min (50 mm/min)  
<sup>2</sup> 0.051 in/min (1.3 mm/min)

**Notes**  
 These are typical property values not to be construed as specification limits.