



Technical Data Sheet

Primefin V500TL20HS

Polypropylene
 LyondellBasell Industries
 Engineering Plastics

Product Description

20% Talc Reinforced, Heat Stabilized Homopolymer Polypropylene

Colors Available
 Meets ESA-M4D293-B

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Talc, 20% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238

Notes

These are typical property values not to be construed as specification limits.