



Pro-fax 7531

Polypropylene, Impact Copolymer

Product Description

Pro-fax 7531 impact polypropylene copolymer is available in pellet form. This resin is typically used injection molding and extrusion applications and offers good cold temperature impact resistance

For regulatory compliance information see Pro-fax 7531 Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Commercial: Active
Test Method used	ASTM
Availability	North America
Processing Methods	Extrusion Thermoforming, Injection Molding
Features	Good Impact Resistance , Good Stiffness
Typical Customer Applications	Opaque Containers

Typical Properties	Method	Value	Unit
Physical			
Density -Specific Gravity <i>Note: 23/23°C Method B</i>	ASTM D 792	0.90	
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	4	g/10 min
Mechanical			
Flexural Modulus (0.05 in/min, 1% Secant, Procedure A) (1.3 mm/min, 1% Secant, Procedure A)	ASTM D 790	180000 1240	psi MPa
Tensile Strength @ Yield (2 in/min) (50 mm/min)	ASTM D 638	4000 28	psi MPa
Tensile Elongation @ Yield	ASTM D 638	9	%
Impact			
Notched Izod Impact (73 °F, Method A) (23 °C, Method A)	ASTM D 256	1.6 85	ft-lb/in J/m
Thermal			
Deformation Temperature Under Load (66 psi) (0.45 MPa) <i>Note: Unannealed</i>	ASTM D 648	180 82	°F °C

Notes

Typical properties; not to be construed as specifications.