

## Technical Data Sheet

### *Pro-fax* RP382U



Polypropylene, Random Copolymer

#### Product Description

*Pro-fax* RP382U clarified, easy molding, very high flow polypropylene random copolymer is available in pellet form. This resin is typically used in injection molding applications requiring excellent processability and good see-through and contact clarity.

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Clear Containers; Multi Media Packaging
<b>Market</b>	Rigid Packaging
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Contains Antistat; High Flow; Medium Clarity

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (230 °C/2.16 kg)	80	g/10 min	80	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm <sup>3</sup>	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	135000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			930	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4000	psi			ASTM D638
(50 mm/min)			28	MPa	ASTM D638
Tensile Elongation at Yield	13	%	13	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength					
(73 °F, Method A)	0.8	ft-lb/in			ASTM D256
(23 °C, Method A)			43	J/m	ASTM D256
<b>Thermal</b>					
Deflection Temperature Under Load					
(66 psi, Unannealed)	172	°F			ASTM D648
(0.45 MPa, Unannealed)			78	°C	ASTM D648
<b>Optical</b>					
Haze, (45 mil)	11	%	11	%	ASTM D1003