

## Technical Data Sheet

### *Pro-fax* SB786



Polypropylene, Impact Copolymer

#### Product Description

*Pro-fax* SB786 impact polypropylene copolymer is available in pellet form. This resin is typically used in injection molding applications and offers good cold temperature impact and blush resistance.

ASTM and ISO-based versions of the technical data sheet are available for *Pro-fax* SB786.

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Battery Cases
<b>Market</b>	Automotive; Industrial Packaging
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Blush Resistant; Good Stiffness; Low Temperature Impact Resistance

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (230 °C/2.16 kg)	8.0	g/10 min	8.0	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm <sup>3</sup>	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	160000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1100	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3700	psi			ASTM D638
(50 mm/min)			26	MPa	ASTM D638
Tensile Elongation at Yield	8	%	8	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength					
(73 °F, Method A)	1.6	ft-lb/in			ASTM D256
(23 °C, Method A)			85	J/m	ASTM D256
<b>Thermal</b>					
Deflection Temperature Under Load					
(66 psi, Unannealed)	175	°F			ASTM D648
(0.45 MPa, Unannealed)			79	°C	ASTM D648

## Notes

These are typical property values not to be construed as specification limits.

### Automotive Specifications

- ▶ FCA MS-DB500 CPN 4168
- ▶ FCA MS-DB500 CPN 4467
- ▶ Ford ESB-M4D175-A
- ▶ Ford WSB-M4D638-A