

Technical Data Sheet

Pro-fax SC973Y



Polypropylene, Impact Copolymer

Product Description

Pro-fax SC973Y high melt flow, impact polypropylene copolymer is available in pellet form. This resin is typically used in thin-wall injection molding applications and offers a very good stiffness/impact balance.

Status	Commercial: Active
Availability	North America
Application	Multi Media Packaging; TWIM Food Containers
Market	Consumer Products; Rigid Packaging
Processing Method	Compounding; Injection Molding
Attribute	Contains Antistat; Good Impact Resistance; Good Stiffness; High Flow; Nucleated

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	107	g/10 min	107	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	205000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1410	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3800	psi			ASTM D638
(50 mm/min)			26	MPa	ASTM D638
Tensile Elongation at Yield	4	%	4	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.7	ft-lb/in			ASTM D256
(23 °C, Method A)			37	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	243	°F			ASTM D648
(0.45 MPa, Unannealed)			117	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.