

## Technical Data Sheet

### *Pro-fax* SR257M



Polypropylene, Random Copolymer

#### Product Description

*Pro-fax* SR257M clarified polypropylene random copolymer is available in pellet form. This resin is typically used in blow molding and extrusion applications and offers excellent see-through and contact clarity.

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Bottles For Consumer Goods; Clear Containers; Food Packaging Film; Specialty Film
<b>Market</b>	Flexible Packaging; Rigid Packaging
<b>Processing Method</b>	Blown Film; Extrusion Blow Molding; Injection Blow Molding; Sheet; Thermoforming
<b>Attribute</b>	Contains Antistat; High Clarity; Random Copolymer

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (230 °C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm <sup>3</sup>	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	140000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			965	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4300	psi			ASTM D638
(50 mm/min)			30	MPa	ASTM D638
Tensile Elongation at Yield	14	%	14	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength					
(73 °F, Method A)	7.0	ft-lb/in			ASTM D256
(23 °C, Method A)			370	J/m	ASTM D256
<b>Thermal</b>					
Deflection Temperature Under Load					
(66 psi, Unannealed)	165	°F			ASTM D648
(0.45 MPa, Unannealed)			74	°C	ASTM D648
<b>Optical</b>					
Haze, (45 mil)	9	%	9	%	ASTM D1003

#### Notes

These are typical property values not to be construed as specification limits.