

## Technical Data Sheet

# Qestron PKS 2165D NAT



Polypropylene Compounds

### Product Description

*Qestron* PKS 2165D NAT is a Polypropylen based coupling agent film for different adhesive applications. The thickness of foil is 32µm and softening point of coupling agent is 119°C.

Additional information:

The weight per unit area is 0.287g/100cm<sup>3</sup>

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Lamination Film
<b>Market</b>	Coupling Agents
<b>Processing Method</b>	Blown Film

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density, (23 °C)	0.898	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Film</b>			
Tensile Strength at Break			
MD	30	MPa	ISO 527-1, -3
TD	15	MPa	ISO 527-1, -3
Tensile Elongation at Break			
MD	>400	%	ISO 527-1, -3
TD	>400	%	ISO 527-1, -3