

Technical Data Sheet

Sequel 1440-UV WA3 BLACK



Polypropylene Compounds

Product Description

Sequel 1440-UV WA3 BLACK engineered polyolefin material is typically used for large automotive exterior applications that require ductile impact properties at low temperatures, has excellent part appearance and processability.

Application	Bumpers; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16.7	g/10 min	ISO 1133-1
Density, (23 °C)	0.94	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C, 2 mm/min)	1050	MPa	ISO 178
Tensile Stress at Yield, (23 °C, 50 mm/min)	20	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	28	kJ/m ²	ISO 180
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			