

Technical Data Sheet

Sequel 1480-PUV KX7 BLACK



Polypropylene Compounds

Product Description

Sequel 1480-PUV KX7 BLACK is a high melt flow, medium modulus, UV-stabilized thermoplastic elastomeric olefin resin (TEO) that has an excellent balance of properties and processability.

Application	Bumpers; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Flow; UV Stabilized

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	26	g/10 min	ASTM D1238
Density, (23 °C, Method A)	0.94	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	1200	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.