

## Technical Data Sheet

**Sequel 1480-PUV XS9 MET**

Polypropylene Compounds

**Product Description**

*Sequel 1480-PUV XS9 MET* is a high melt flow, medium modulus, UV-stabilized thermoplastic elastomeric olefin resin (TEO) that has an excellent balance of properties and processability.

<b>Status</b>	Developmental
<b>Availability</b>	North America
<b>Application</b>	Exterior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	High Flow; UV Stabilized

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	27	g/10 min	ASTM D1238
Density, (23 °C, Method A)	0.96	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1350	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	23	MPa	ISO 527-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			