



Sequel 1980-PUV

Compounded Polyolefin

Product Description

Sequel 1980-PUV high melt flow, high flexural modulus, UV-stabilized, mineral-filled, thermoplastic elastomeric olefin has an excellent balance of properties and processability.

Product Characteristics

Test Method used	ISO
Processing Methods	Injection Molding
Features	Good Flow, Good Moldability, Good Weather Resistance
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	25	g/10 min
Density (Method A)	ISO 1183	1.04	g/cm ³
Mechanical			
Flexural modulus (23 °C)	ISO 178	1700	MPa
Additional Information			
Mold shrinkage	ISO 294-4		