



Sequel 2392 SP

Compounded Polyolefin

Product Description

Sequel 2392 SP thermoplastic polyolefin material is designed for molded-in-color automotive interior applications that require stiffness and dimensional stability.

Product Characteristics

Status	Commercial: Restricted
Test Method used	ASTM
Availability	North America
Processing Methods	Injection Molding
Features	Pleasing Surface Appearance, Good Dimensional Stability, Good Processability, Good Stiffness
Typical Customer Applications	Interior Applications

Typical Properties	Method	Value	Unit
Physical			
Density -Specific Gravity	ASTM D 792	0.93	
Melt Flow Rate	ASTM D 1238	50	g/10 min
Mechanical			
Flexural Modulus (30 mm/min, 23 °C)	ASTM D 790	2160	MPa
Tensile Strength @ Yield	ASTM D 638	26	MPa
<i>Note: Test speed: 30 mm/min</i>			
Tensile Elongation @ Brk	ASTM D 638	50	%
<i>Note: Test Speed: 30 mm/min</i>			
Flexural Strength	ASTM D 790	40	MPa
<i>Note: Test Speed: 30 mm/min</i>			
Impact			
Notched Izod Impact	ASTM D 256		
(-30 °C)		30	J/m
(23 °C)		55	J/m
Hardness			
Rockwell Hardness	ASTM D 785	90	
Thermal			
Heat deflection temperature A	ISO 75/ASTM D 72 648		°C
Heat deflection temperature B	ISO 75/ASTM D 130 648		°C

Notes

Typical properties; not to be construed as specifications.