

Technical Data Sheet

**Softell TKG 259N G21385**



Polypropylene Compounds

**Product Description**

Softell TKG 259N G21385 is a glass fiber reinforced PP copolymer, with high stiffness, excellent scratch resistance, superior dimensional stability and low gloss. The product is also available as a customized color matched, pellet form. This grade is delivered in G21385 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Status</b>	Commercial: Active
<b>Availability</b>	Europe
<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Processability; Soft

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1
<b>Impact</b>			
Notched Izod Impact Strength, (-30 °C)	7	kJ/m <sup>2</sup>	ISO 180/1A