

## Technical Data Sheet

### *Softell* TKG 300N 2 NAT



Polypropylene Compounds

#### Product Description

*Softell* TKG 300N 2 NAT is a 25% glass fiber reinforced PP copolymer, with high stiffness, excellent scratch resistance, high dimensional stability and low gloss. Product is available as natural, pellet form

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Dimensional Stability; High Stiffness; Low Gloss; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	1.09	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2500	MPa	ISO 178/A1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	35	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	7.5	kJ/m <sup>2</sup>	ISO 179-1/1eA