

## Technical Data Sheet

**Softell TKG 300N G32832**

Polypropylene Compounds

**Product Description**

Softell TKG 300N G32832 is a 25% glass fiber reinforced PP copolymer, with excellent scratch resistance and very good impact/stiffness balance. The product is available in different color matched, pellet form

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	1.09	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2500	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	33	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	37	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	7	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	130	°C	ISO 75B-1, -2