

## Technical Data Sheet

### Softell TKG 317N C12507



Polypropylene Compounds

#### Product Description

Softell TKG 317N C12507 is a 25% glass fiber reinforced PP copolymer, with high dimensional stability, good surface appearance, low gloss, high stiffness and excellent scratch resistance.

Please contact lyondellbasell for shrinkage recommendations. This grade is delivered in C12507 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Automotive Parts; Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Processability; High Impact Resistance; High Stiffness; Noise Damping; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ISO 1133-1
Density, (23 °C)	1.09	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	4500	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	57	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)	6	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	10	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	5	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	128	°C	ISO 75A-1, -2