

Technical Data Sheet

Bmc 851

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Creep Resistant	• Good Impact Resistance	
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.75	1.74 g/cm ³	ASTM D792

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	6000 psi	41.4 MPa	ASTM D638
Flexural Modulus	1.80E+6 psi	12400 MPa	ASTM D790
Flexural Strength (Yield)	15000 psi	103 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	6.0 ft·lb/in	320 J/m	ASTM D256

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	40	40	ASTM D2583

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating	V-0	V-0	UL 94

Notes

These are typical property values not to be construed as specification limits.