

Technical Data Sheet

Bmc 901

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

Product Description

BMC 901 is an encapsulation grade, soft flow material. As with all other BMCI compounds, this Series can be supplied in logs, slugs or bulk. Typical applications are electrical coil encapsulations and armature shafts.

General

Uses	• Coating Applications	• Electrical/Electronic Applications
Forms	• BMC - Bulk Molding Compound	
Processing Method	• Compression Molding	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.91	1.91 g/cm ³	ASTM D792
Water Absorption (24 Hr, 73°F (23°C))	0.15 %	0.15 %	ASTM D570
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	5500 psi	37.9 MPa	ASTM D638
Flexural Modulus	1.65E+6 psi	11400 MPa	ASTM D790
Flexural Strength	11000 psi	75.8 MPa	ASTM D790
Compressive Strength	19000 psi	131 MPa	ASTM D695
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.0 ft·lb/in	160 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	40	40	ASTM D2583
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	400 °F	204 °C	ASTM D648
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Dielectric Strength (Method A (short-time))	350 V/mil	14 kV/mm	ASTM D149
Arc Resistance	180 sec	180 sec	ASTM D495
Comparative Tracking Index (CTI)	500 V	500 V	UL 746A
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.6 Mm))	HB	HB	UL 94

Technical Data Sheet

Bmc 901

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Mold Temperature	280 to 330 °F	138 to 166 °C

Notes

These are typical property values not to be construed as specification limits.