

Technical Data Sheet

Bmc HT12-1026

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

General		
Uses	• Automotive Applications	• Automotive Under the Hood
Appearance	• Black	
Forms	• Pellets	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.85	1.85 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	10800 psi	74.5 MPa	ASTM D638
Flexural Modulus	1.90E+6 psi	13100 MPa	ASTM D790
Flexural Strength (Yield)	21500 psi	148 MPa	ASTM D790
Compressive Strength	23600 psi	163 MPa	ASTM D695
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Unnotched Izod Impact	6.1 ft·lb/in	330 J/m	ASTM D4812
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	33	33	ASTM D2583
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Dielectric Strength	370 V/mil	15 kV/mm	ASTM D149
Arc Resistance	180 sec	180 sec	ASTM D495
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 In (1.5 Mm)	HB	HB	
0.09 In (2.2 Mm)	HB	HB	
0.12 In (3.1 Mm)	HB	HB	

Additional Information	
Barcol Hardness, ASTM D2583: 30 to 35	
UL Flame Rating, UL 94, 0.058 to 0.062 in: HB	
UL Flame Rating, UL 94, 0.075 to 0.1 in: HB	
UL Flame Rating, UL 94, 0.120 to 0.125 in: HB	

Notes

¹ Type I

Notes

These are typical property values not to be construed as specification limits.