

Technical Data Sheet

Bmc T40(18)-LS

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

General	
Features	• High Strength
Uses	• Electrical/Electronic Applications
Appearance	• Grey
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.82	1.82 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	9990 psi	68.8 MPa	ASTM D638
Flexural Modulus	2.20E+6 psi	15200 MPa	ASTM D790
Flexural Strength (Yield)	28500 psi	197 MPa	ASTM D790
Compressive Strength	20700 psi	143 MPa	ASTM D695
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Unnotched Izod Impact	8.0 ft·lb/in	430 J/m	ASTM D4812
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	23	23	ASTM D2583
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Dielectric Strength	390 V/mil	15 kV/mm	ASTM D149
Arc Resistance	190 sec	190 sec	ASTM D495
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.09 In (2.2 Mm)	V-0	V-0	
0.12 In (3.1 Mm)	5VA	5VA	

Additional Information	
Barcol Hardness, ASTM D2583: 20 to 25	
UL Flame Rating, UL 94, 0.075 to 0.1 in: V-0	
UL Flame Rating, UL 94, 0.120 to 0.125 in: 5-VA	

Notes
¹ Type I

Notes
These are typical property values not to be construed as specification limits.