

Technical Data Sheet

Rxloy NEV00NR03NA

Polypropylene Alloy
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------|-----------------|
| Appearance | • Natural Color |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	0.892	0.890 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield)	1200 psi	8.27 MPa	ASTM D638
Tensile Elongation (Break)	810 %	810 %	ASTM D638
Flexural Strength (Yield)	800 psi	5.52 MPa	ASTM D790

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Durometer Hardness (Shore A)	72	72	ASTM D2240
------------------------------	----	----	------------

Notes

These are typical property values not to be construed as specification limits.