

Technical Data Sheet

Accucomp CP0402L

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General

Forms • Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.900	0.898 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	1.6 g/10 min	1.6 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	145000 psi	1000 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	3770 psi	26.0 MPa	
Break	2900 psi	20.0 MPa	
Tensile Elongation			ASTM D638
Yield	10 %	10 %	
Break	400 %	400 %	
Flexural Modulus	160000 psi	1100 MPa	ASTM D790
Flexural Strength	4500 psi	31.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
0.125 In (3.18 Mm)	15 ft·lb/in	820 J/m	
0.250 In (6.35 Mm)	13 ft·lb/in	680 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	70	70	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	181 °F	83.0 °C	
264 Psi (1.8 Mpa), Unannealed	154 °F	68.0 °C	

Notes

These are typical property values not to be construed as specification limits.