

Technical Data Sheet

# Accutech CP0436C10L

Polypropylene Copolymer  
 LyondellBasell Industries  
 Engineering Plastics

**General**

Filler / Reinforcement	• Calcium Carbonate, 10% Filler by Weight
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.920	0.918 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	11 g/10 min	11 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	174000 psi	1200 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	3190 psi	22.0 MPa	
Break	2610 psi	18.0 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	170 %	170 %	
Flexural Modulus	145000 psi	1000 MPa	ASTM D790
Flexural Strength	3630 psi	25.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.4 ft·lb/in	130 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	68	68	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	127 °F	53.0 °C	
264 Psi (1.8 Mpa), Unannealed	190 °F	88.0 °C	

**Additional Information**

Ash Content, ASTM D2584: 10%

**Notes**

These are typical property values not to be construed as specification limits.