

Technical Data Sheet

Accutech CP0436G10M20CL

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General

- Filler / Reinforcement • Glass Fiber, 10% Filler by Weight • Mineral, 20% Filler by Weight
- Forms • Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.11	1.11 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	392000 psi	2700 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	4350 psi	30.0 MPa	
Break	4060 psi	28.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	8.0 %	8.0 %	
Flexural Modulus	486000 psi	3350 MPa	ASTM D790
Flexural Strength	6670 psi	46.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.9 ft·lb/in	100 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	55	55	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	293 °F	145 °C	
264 Psi (1.8 Mpa), Unannealed	217 °F	103 °C	

Additional Information

Ash Content, ASTM D2584: 30%

Notes

These are typical property values not to be construed as specification limits.