

Technical Data Sheet

Accutech CP0436T10L1

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------------------|------------------------------|
| Filler / Reinforcement | • Talc, 10% Filler by Weight |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	0.960	0.958 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	12 g/10 min	12 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	203000 psi	1400 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	3340 psi	23.0 MPa	
Break	2470 psi	17.0 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	30 %	30 %	
Flexural Modulus	203000 psi	1400 MPa	ASTM D790
Flexural Strength	4210 psi	29.0 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact	1.9 ft·lb/in	100 J/m	ASTM D256
---------------------	--------------	---------	-----------

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Rockwell Hardness (R-scale)	63	63	ASTM D785
-----------------------------	----	----	-----------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	212 °F	100 °C	
264 Psi (1.8 Mpa), Unannealed	127 °F	53.0 °C	

Additional Information

Ash Content, ASTM D2584: 10%

Notes

These are typical property values not to be construed as specification limits.