

## Technical Data Sheet

# Accutech CP0436T20L

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

General			
Filler / Reinforcement	• Talc, 20% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	12 g/10 min	12 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	218000 psi	1500 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	3050 psi	21.0 MPa	
Break	2320 psi	16.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	33 %	33 %	
Flexural Modulus	218000 psi	1500 MPa	ASTM D790
Flexural Strength	4060 psi	28.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.4 ft·lb/in	75 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	55	55	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	212 °F	100 °C	
264 Psi (1.8 Mpa), Unannealed	133 °F	56.0 °C	

Additional Information			
Ash Content, ASTM D2584: 20%			

### Notes

These are typical property values not to be construed as specification limits.