

Technical Data Sheet

# Accutech CP0436W10L

Polypropylene Copolymer  
 LyondellBasell Industries  
 Engineering Plastics

**General**

Filler / Reinforcement	• Wollastonite (CaSiO3), 10% Filler by Weight
Forms	• Pellets

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.960	0.958 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	12 g/10 min	12 g/10 min	ASTM D1238

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	181000 psi	1250 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	3190 psi	22.0 MPa	
Break	2180 psi	15.0 MPa	
Tensile Elongation			ASTM D638
Yield	6.0 %	6.0 %	
Break	40 %	40 %	
Flexural Modulus	160000 psi	1100 MPa	ASTM D790
Flexural Strength	3480 psi	24.0 MPa	ASTM D790

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.2 ft·lb/in	120 J/m	ASTM D256

**Hardness**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	58	58	ASTM D785

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	201 °F	94.0 °C	
264 Psi (1.8 Mpa), Unannealed	124 °F	51.0 °C	

**Additional Information**

Ash Content, ASTM D2584: 10%
------------------------------

**Notes**

These are typical property values not to be construed as specification limits.