

Technical Data Sheet

# Accutech CP0437C20L

Polypropylene Copolymer  
 LyondellBasell Industries  
 Engineering Plastics

**General**

Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.03	1.03 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	20 g/10 min	20 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	160000 psi	1100 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	2030 psi	14.0 MPa	
Break	1740 psi	12.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	90 %	90 %	
Flexural Modulus	145000 psi	1000 MPa	ASTM D790
Flexural Strength	2320 psi	16.0 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact	10 ft·lb/in	560 J/m	ASTM D256
---------------------	-------------	---------	-----------

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Rockwell Hardness (R-scale)	50	50	ASTM D785
-----------------------------	----	----	-----------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	122 °F	50.0 °C	
264 Psi (1.8 Mpa), Unannealed	167 °F	75.0 °C	

**Additional Information**

Ash Content, ASTM D2584: 20%

**Notes**

These are typical property values not to be construed as specification limits.