

Technical Data Sheet

# Accutech CP0437G20M10CL

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

**General**

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight • Mineral, 10% Filler by Weight
Forms	• Pellets

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	421000 psi	2900 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	5370 psi	37.0 MPa	
Break	5080 psi	35.0 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	9.0 %	9.0 %	
Flexural Modulus	464000 psi	3200 MPa	ASTM D790
Flexural Strength	7540 psi	52.0 MPa	ASTM D790

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.9 ft·lb/in	150 J/m	ASTM D256

**Hardness**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	69	69	ASTM D785

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	306 °F	152 °C	
264 Psi (1.8 Mpa), Unannealed	248 °F	120 °C	

**Additional Information**

Ash Content, ASTM D2584: 30%

**Notes**

These are typical property values not to be construed as specification limits.