

Technical Data Sheet

Accutech CP0437G30CL

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General

- Filler / Reinforcement
 - Glass Fiber, 30% Filler by Weight
- Forms
 - Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	493000 psi	3400 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	7250 psi	50.0 MPa	
Break	6960 psi	48.0 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	8.0 %	8.0 %	
Flexural Modulus	595000 psi	4100 MPa	ASTM D790
Flexural Strength	10200 psi	70.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.0 ft-lb/in	160 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	81	81	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	311 °F	155 °C	
264 Psi (1.8 Mpa), Unannealed	266 °F	130 °C	

Additional Information

Ash Content, ASTM D2584: 30%

Notes

These are typical property values not to be construed as specification limits.