

Technical Data Sheet

Accutech CP0437G5M25CL

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics

General

Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 5.0% Filler by Weight Mineral, 25% Filler by Weight
Forms	<ul style="list-style-type: none"> Pellets

Physical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	11 g/10 min	11 g/10 min	ASTM D1238

Mechanical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	348000 psi	2400 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	3190 psi	22.0 MPa	
Break	2900 psi	20.0 MPa	
Tensile Elongation			ASTM D638
Yield	3.0 %	3.0 %	
Break	6.0 %	6.0 %	
Flexural Modulus	363000 psi	2500 MPa	ASTM D790
Flexural Strength	4500 psi	31.0 MPa	ASTM D790

Impact

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.8 ft·lb/in	95 J/m	ASTM D256

Hardness

	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	53	53	ASTM D785

Thermal

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	271 °F	133 °C	
264 Psi (1.8 Mpa), Unannealed	172 °F	78.0 °C	

Additional Information

Ash Content, ASTM D2584: 30%

Notes

These are typical property values not to be construed as specification limits.