

Technical Data Sheet

# Accutech CP0437M20CL

Polypropylene Copolymer  
 LyondellBasell Industries  
 Engineering Plastics

General	
Filler / Reinforcement	• Mica, 20% Filler by Weight
Features	• Chemically Coupled
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.02	1.02 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	15 g/10 min	15 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	247000 psi	1700 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	2470 psi	17.0 MPa	
Break	2180 psi	15.0 MPa	
Tensile Elongation			ASTM D638
Yield	3.0 %	3.0 %	
Break	10 %	10 %	
Flexural Modulus	247000 psi	1700 MPa	ASTM D790
Flexural Strength	3190 psi	22.0 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.8 ft·lb/in	150 J/m	ASTM D256

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	45	45	ASTM D785

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	217 °F	103 °C	
264 Psi (1.8 Mpa), Unannealed	131 °F	55.0 °C	

Additional Information
Ash Content, ASTM D2584: 20%

**Notes**

These are typical property values not to be construed as specification limits.