

Technical Data Sheet

Accutech CP0437M40L

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Mica, 40% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.19	1.19 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	15 g/10 min	15 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	363000 psi	2500 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	2180 psi	15.0 MPa	
Break	2030 psi	14.0 MPa	
Tensile Elongation			ASTM D638
Yield	2.0 %	2.0 %	
Break	6.0 %	6.0 %	
Flexural Modulus	435000 psi	3000 MPa	ASTM D790
Flexural Strength	3190 psi	22.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.9 ft·lb/in	100 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	33	33	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	214 °F	101 °C	
264 Psi (1.8 Mpa), Unannealed	145 °F	63.0 °C	

Additional Information			
Ash Content, ASTM D2584:	40%		

Notes

These are typical property values not to be construed as specification limits.