

Technical Data Sheet

# Accutech CP0437W20L

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Wollastonite (CaSiO <sub>3</sub> ), 20% Filler by Weight
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.03	1.03 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	17 g/10 min	17 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	189000 psi	1300 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	2320 psi	16.0 MPa	
Break	1890 psi	13.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	18 %	18 %	
Flexural Modulus	174000 psi	1200 MPa	ASTM D790
Flexural Strength	2760 psi	19.0 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.2 ft·lb/in	170 J/m	ASTM D256

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	58	58	ASTM D785

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	180 °F	82.0 °C	
264 Psi (1.8 Mpa), Unannealed	126 °F	52.0 °C	

Additional Information
Ash Content, ASTM D2584: 20%

**Notes**

These are typical property values not to be construed as specification limits.