

Technical Data Sheet

# Ferro Pp NPP00GE07NA

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

**General**

Features	• Copolymer
Forms	• Pellets
Processing Method	• Injection Molding

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.900	0.898 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	1.6 g/10 min	1.6 g/10 min	ASTM D1238

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	3200 psi	22.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	300 %	300 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	140000 psi	965 MPa	
Tangent : 73°F (23°C)	150000 psi	1030 MPa	
Flexural Strength (Yield, 73°F (23°C))	3700 psi	25.5 MPa	ASTM D790

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D256
Gardner Impact	250 in·lb	28.2 J	ASTM D5420

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	160 °F	71.1 °C	
264 Psi (1.8 Mpa), Unannealed	120 °F	48.9 °C	

Technical Data Sheet

**Ferro Pp NPP00GE07NA**

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.