

Technical Data Sheet

Ferro Pp NPP00GX06NA

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General	
Additive	• UV Stabilizer
Features	• Copolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.900	0.898 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	0.70 g/10 min	0.70 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	3800 psi	26.2 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	350 %	350 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	132000 psi	910 MPa	
Tangent : 73°F (23°C)	143000 psi	986 MPa	
Flexural Strength (Yield, 73°F (23°C))	4300 psi	29.6 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	15 ft·lb/in	780 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D4812
Gardner Impact	311 in·lb	35.1 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	190 °F	87.8 °C	
264 Psi (1.8 Mpa), Unannealed	125 °F	51.7 °C	

Technical Data Sheet

Ferro Pp NPP00GX06NA

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.