

Technical Data Sheet

# Ferro Pp NPP00GX12BK

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

General	
Features	• Copolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.900	0.898 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	2800 psi	19.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	70 %	70 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	124000 psi	855 MPa	
Tangent : 73°F (23°C)	134000 psi	924 MPa	
Flexural Strength (Yield, 73°F (23°C))	3700 psi	25.5 MPa	ASTM D790


Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	11 ft·lb/in	590 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D4812
Gardner Impact	285 in·lb	32.2 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	165 °F	73.9 °C	
264 Psi (1.8 Mpa), Unannealed	115 °F	46.1 °C	

Technical Data Sheet

# Ferro Pp NPP00GX12BK

Polypropylene Copolymer  
 LyondellBasell Industries  
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.