

Technical Data Sheet

Ferro Pp NPP99GB09BK

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics

General	
Features	• Copolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.910	0.908 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	14 g/10 min	14 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	3200 psi	22.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	300 %	300 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	129000 psi	889 MPa	
Tangent : 73°F (23°C)	135000 psi	931 MPa	
Flexural Strength (Yield, 73°F (23°C))	3900 psi	26.9 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	2.4 ft·lb/in	130 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D4812
Gardner Impact	250 in·lb	28.2 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	178 °F	81.1 °C	
264 Psi (1.8 Mpa), Unannealed	115 °F	46.1 °C	

Technical Data Sheet

Ferro Pp NPP99GB09BK

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.