

Technical Data Sheet

# Ferro Pp TPP25AP94NA

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Talc, 25% Filler by Weight
Additive	• UV Stabilizer
Features	• Copolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	20 g/10 min	20 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength <sup>1</sup> (Yield, 73°F (23°C))	3650 psi	25.2 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	25 %	25 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	239000 psi	1650 MPa	
Tangent : 73°F (23°C)	281000 psi	1940 MPa	
Flexural Strength <sup>2</sup> (Yield, 73°F (23°C))	4950 psi	34.1 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.5 ft·lb/in	82 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	
264 Psi (1.8 Mpa), Unannealed	133 °F	56.0 °C	

Additional Information
Filler Content, ASTM D2584: 25%

Technical Data Sheet

**Ferro Pp TPP25AP94NA**

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C



## Technical Data Sheet

# ***Ferro Pp* TPP25AP94NA**

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

### Notes

<sup>1</sup> 20 in/min (500 mm/min)

<sup>2</sup> 0.051 in/min (1.3 mm/min)

---

### Notes

These are typical property values not to be construed as specification limits.