

Technical Data Sheet

Fiberfil PP-61/VO/NH

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Features	• Copolymer	• Flame Retardant	• Halogen Free
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 to 14 g/10 min	10 to 14 g/10 min	ASTM D1238
Water Absorption (24 Hr)	0.020 %	0.020 %	ASTM D570

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	250000 psi	1720 MPa	ASTM D638
Tensile Strength (73°F (23°C))	2800 psi	19.3 MPa	ASTM D638
Tensile Elongation (Yield, 73°F (23°C))	13 %	13 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	220000 psi	1520 MPa	ASTM D790
Flexural Strength (73°F (23°C))	3200 psi	22.1 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	1.0 ft-lb/in	53 J/m	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	80 to 90	80 to 90	ASTM D785

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	160 °F	71.1 °C	
264 Psi (1.8 Mpa), Unannealed	145 °F	62.8 °C	

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

Technical Data Sheet

Fiberfil PP-61/VO/NH

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	170 °F	77 °C
Drying Time	2.0 hr	2.0 hr
Suggested Max Moisture	0.20 %	0.20 %
Rear Temperature	360 to 390 °F	182 to 199 °C
Middle Temperature	380 to 410 °F	193 to 210 °C
Front Temperature	370 to 400 °F	188 to 204 °C
Nozzle Temperature	360 to 380 °F	182 to 193 °C
Processing (Melt) Temp	380 to 420 °F	193 to 216 °C
Mold Temperature	90 to 160 °F	32 to 71 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa

Injection Notes

Screw speed: Slow to Medium

Notes

These are typical property values not to be construed as specification limits.