

Technical Data Sheet
ICORENE® 4014WF
 Polypropylene Copolymer
 Rotomolding



Product Description

ICORENE® 4014WF is a polypropylene copolymer that has been specifically developed for rotational moulding.

This grade is UV stabilised and has improved impact resistance.

ICORENE® 4014WF is suitable for applications requiring high stiffness and high temperature resistance.

General

Additive	• UV Stabilizer		
Features	• Good Impact Resistance	• High Stiffness	• UV Resistant
Uses	• Automotive Under the Hood	• Displays	• High Temperature Applications
Appearance	• Natural Color	• Unspecified Color	
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.900 g/cm ³	0.900 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15 g/10 min	15 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield	3050 psi	21.0 MPa	
Break	3050 psi	21.0 MPa	
Tensile Elongation			ASTM D638
Yield	13 %	13 %	
Break	97 %	97 %	
Flexural Modulus	174000 psi	1200 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹			Internal Method
32°F (0°C)	1.91 in-lb/mil	85.0 J/cm	
73°F (23°C)	2.81 in-lb/mil	125 J/cm	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	194 °F	90.0 °C	
264 psi (1.8 MPa), Unannealed	122 °F	50.0 °C	
Melting Temperature	329 °F	165 °C	DSC

Notes

¹ based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.