

Technical Data Sheet

Matrixx PP3C0

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics

Product Description

Matrixx PP3C0 is a High Flow Polypropylene Copolymer

General

Features	• Copolymer
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	0.910	0.908 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	18 g/10 min	18 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield, 73°F (23°C))	3800 psi	26.2 MPa	ASTM D638
Flexural Modulus - Tangent	180000 psi	1240 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	2.0 ft·lb/in	110 J/m	
Gardner Impact	170 in·lb	19.2 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	170 °F	76.7 °C	
264 Psi (1.8 Mpa), Unannealed	110 °F	43.3 °C	

Additional Information

1E9W1A/PR2399
 Revision: 5/2/2020

Technical Data Sheet

Matrixx PP3C0

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	350 to 450 °F	177 to 232 °C
Middle Temperature	350 to 450 °F	177 to 232 °C
Front Temperature	350 to 450 °F	177 to 232 °C
Processing (Melt) Temp	380 to 450 °F	193 to 232 °C
Mold Temperature	70 to 120 °F	21 to 49 °C
Injection Rate	Moderate	Moderate
Back Pressure	20.0 to 300 psi	0.138 to 2.07 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

- Drying not normally required
- Screw Speed: Slow to Medium
- Injection Booster Pressure: Maximum without flash, 60% of machine maximum, target

Notes

These are typical property values not to be construed as specification limits.