

Technical Data Sheet

Matrixx FPP2B25CC

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics

Product Description
 FPP2B25CC is a 25% Glass-Reinforced, Chemically Coupled, Copolymer Polypropylene

General	
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Features	• Chemically Coupled
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	7.0 g/10 min	7.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	8200 psi	56.5 MPa	ASTM D638
Flexural Modulus - Tangent	525000 psi	3620 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 In (3.18 Mm)	3.4 ft·lb/in	180 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	ASTM D648
264 Psi (1.8 Mpa), Unannealed	265 °F	129 °C	

Additional Information
 1E9F3A0/PR1383
 Revision: 5/2/2020

Technical Data Sheet

Matrixx FPP2B25CC

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	390 to 470 °F	199 to 243 °C
Middle Temperature	390 to 470 °F	199 to 243 °C
Front Temperature	390 to 470 °F	199 to 243 °C
Processing (Melt) Temp	390 to 470 °F	199 to 243 °C
Mold Temperature	60 to 150 °F	16 to 66 °C
Injection Rate	Moderate	Moderate
Back Pressure	< 50.0 psi	< 0.345 MPa
Screw Speed	20 to 60 rpm	20 to 60 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes
 Drying not normally required

Notes

These are typical property values not to be construed as specification limits.