



Technical Data Sheet

Matrixx FPP3B35WU

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics

Product Description

FPP3B35WU is a 35% Glass-Reinforced, Weather Resistant, Copolymer Polypropylene

General

Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Features	• Copolymer
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.17	1.17 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield, 73°F (23°C))	10000 psi	68.9 MPa	ASTM D638
Tensile Elongation (Yield)	4.0 %	4.0 %	ASTM D638
Flexural Modulus - Tangent	750000 psi	5170 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	2.9 ft·lb/in	150 J/m	

Technical Data Sheet

Matrixx FPP3B35WU

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	390 to 470 °F	199 to 243 °C
Middle Temperature	390 to 470 °F	199 to 243 °C
Front Temperature	390 to 470 °F	199 to 243 °C
Processing (Melt) Temp	390 to 470 °F	199 to 243 °C
Mold Temperature	60 to 150 °F	16 to 66 °C
Injection Rate	Moderate	Moderate
Back Pressure	< 50.0 psi	< 0.345 MPa
Screw Speed	20 to 60 rpm	20 to 60 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

Drying not normally required

Notes

These are typical property values not to be construed as specification limits.