

Technical Data Sheet

Polyflam RIPP 2000 E S

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description

Unfilled flame retardant PP-Copolymer grade for extrusion or blow moulding, UV stabilized for outdoor applications, halogen free acc. DIN VDE 0472 part 815

General

Features	<ul style="list-style-type: none"> Flame Retardant Good Colorability 	<ul style="list-style-type: none"> Halogen Free High Viscosity
UL File Number	E86615	
Processing Method	<ul style="list-style-type: none"> Blow Molding 	<ul style="list-style-type: none"> Extrusion Injection Molding
Resin ID (ISO 1043)	PP FR(40)	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density	0.930 g/cm ³	0.930 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	2.5 cm ³ /10min	2.5 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	174000 psi	1200 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	3920 psi	27.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	10 %	10 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	1.4 ft·lb/in ²	3.0 kJ/m ²	
73°F (23°C)	10 ft·lb/in ²	22 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	29 ft·lb/in ²	60 kJ/m ²	
73°F (23°C)	No Break	No Break	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	194 °F	90.0 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	118 °F	48.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	154 °F	68.0 °C	ISO 306/B50
--	298 °F	148 °C	ISO 306/A50
Ball Pressure Test (266°F (130°C))	Pass	Pass	IEC 60695-10-2
RTI Elec			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Imp			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Str			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	

Technical Data Sheet

Polyflam RIPP 2000 E S


Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.06 In (1.5 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Hot-wire Ignition (HWI)			UL 746A
0.06 In (1.5 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
Flame Rating			UL 94 IEC 60695-11-10, -20
0.030 In (0.75 Mm)	V-2	V-2	
0.06 In (1.5 Mm)	V-2	V-2	
0.12 In (3.0 Mm)	V-2	V-2	
Glow Wire Flammability Index			IEC 60695-2-12
0.030 In (0.75 Mm)	1760 °F	960 °C	
0.06 In (1.5 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 In (0.75 Mm)	1290 °F	700 °C	
0.06 In (1.5 Mm)	1560 °F	850 °C	
0.12 In (3.0 Mm)	1470 °F	800 °C	
Oxygen Index	25 %	25 %	ISO 4589-2

Technical Data Sheet

Polyflam RIPP 2000 E S

Polypropylene Copolymer
 LyondellBasell Industries
 Engineering Plastics




Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	356 °F	180 °C
Middle Temperature	392 °F	200 °C
Front Temperature	410 °F	210 °C
Nozzle Temperature	428 °F	220 °C
Processing (Melt) Temp	356 to 410 °F	180 to 210 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Pressure	11600 to 17400 psi	80.0 to 120 MPa
Injection Rate	Slow-Moderate	Slow-Moderate
Holding Pressure	5800 to 13100 psi	40.0 to 90.0 MPa
Back Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Cushion	< 0.197 in	< 5.00 mm
Screw Speed	< 709 in/min	< 18 m/min

Technical Data Sheet

Polyflam RIPP 2000 E S

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Extrusion	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	< 0.10 %	< 0.10 %
Melt Temperature	338 to 410 °F	170 to 210 °C

Notes

These are typical property values not to be construed as specification limits.