

Technical Data Sheet

Polyflam RIPP 3125

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description
25% talc filled flame retardant PP copolymer compound without PBDE

General			
Filler / Reinforcement	• Talc, 25% Filler by Weight		
Features	• Copolymer	• Flame Retardant	
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.40 g/cm ³	1.40 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	12 cm ³ /10min	12 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	348000 psi	2400 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	2470 psi	17.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	2.0 %	2.0 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	0.95 ft·lb/in ²	2.0 kJ/m ²	
73°F (23°C)	4.8 ft·lb/in ²	10 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	6.2 ft·lb/in ²	13 kJ/m ²	
73°F (23°C)	18 ft·lb/in ²	37 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	207 °F	97.0 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	135 °F	57.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	136 °F	58.0 °C	ISO 306/B50
--	280 °F	138 °C	ISO 306/A120
Ball Pressure Test (212°F (100°C))	Pass	Pass	IEC 60695-10-2


Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.6 Mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1250 °F	675 °C	
0.12 In (3.0 Mm)	1250 °F	675 °C	
Oxygen Index	27 %	27 %	ISO 4589-2

Technical Data Sheet

Polyflam RIPP 3125

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.