

Technical Data Sheet

Polyflam RIPP 4000

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description

Unfilled flame-retardant PP-Copolymer, halogenfree

General

Features	<ul style="list-style-type: none"> Copolymer Flame Retardant 	<ul style="list-style-type: none"> Good Processability Halogen Free
UL File Number	<ul style="list-style-type: none"> E86615 	
Processing Method	<ul style="list-style-type: none"> Injection Molding 	
Resin ID (ISO 1043)	<ul style="list-style-type: none"> PP FR(51) 	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	13 cm ³ /10min	13 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	319000 psi	2200 MPa	ISO 527-1/1A/1
Tensile Stress			ISO 527-2/1A/50
Yield	2900 psi	20.0 MPa	
Break	2280 psi	15.7 MPa	
Tensile Strain (Yield)	3.2 %	3.2 %	ISO 527-2/1A/50
Nominal Tensile Strain at Break	27 %	27 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	1.1 ft·lb/in ²	2.3 kJ/m ²	
73°F (23°C)	1.9 ft·lb/in ²	4.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	7.7 ft·lb/in ²	16 kJ/m ²	
73°F (23°C)	26 ft·lb/in ²	55 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	207 °F	97.0 °C	ISO 75-2/B
264 Psi (1.8 Mpa), Unannealed	126 °F	52.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	171 °F	77.0 °C	ISO 306/B50
--	304 °F	151 °C	ISO 306/A50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.030 In (0.75 Mm)	PLC 0	PLC 0	
0.06 In (1.5 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Hot-wire Ignition (HWI)			UL 746A
0.030 In (0.75 Mm)	PLC 2	PLC 2	
0.06 In (1.5 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	

Technical Data Sheet

Polyflam RIPP 4000


Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Flammability	Nominal Value (English)		Nominal Value (SI)		Test Method
Burning Rate					
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min		0.0 mm/min		ISO 3795
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min		0.0 mm/min		FMVSS 302
Flame Rating					
0.030 In (0.75 Mm)	V-0		V-0		UL 94 IEC 60695-11-10, -20
0.06 In (1.5 Mm)	V-0		V-0		
0.12 In (3.0 Mm)	•	V-0	•	V-0	
	•	5VA	•	5VA	
Glow Wire Flammability Index					
0.030 In (0.75 Mm)	1760 °F		960 °C		IEC 60695-2-12
0.06 In (1.5 Mm)	1760 °F		960 °C		
0.12 In (3.0 Mm)	1760 °F		960 °C		
Glow Wire Ignition Temperature					
0.030 In (0.75 Mm)	1340 °F		725 °C		IEC 60695-2-13
0.06 In (1.5 Mm)	1340 °F		725 °C		
0.12 In (3.0 Mm)	1380 °F		750 °C		

Technical Data Sheet

Polyflam RIPP 4000

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Pressure	11600 to 17400 psi	80.0 to 120 MPa
Injection Rate	Slow-Moderate	Slow-Moderate
Holding Pressure	5800 to 13100 psi	40.0 to 90.0 MPa
Back Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Screw Speed	< 709 in/min	< 18 m/min

Injection Notes

Predrying

Predrying at 70°C for 2-4 hours is recommended as a precaution.

Reprocessing

Addition of regrind is normally possible, but it must be tested in each case regarding the percentage and requirements of the article. Thermal damage during first processing depends on processing parameters and the geometry of flow path and article.

Shut down

Avoid long melt residence time. Purge with base polymer or with polyolefines.

Finishing

Machining is usually possible.

Notes

These are typical property values not to be construed as specification limits.